


*Indian Standard*  
SPECIFICATION FOR  
SOIL BASED BLOCKS USED IN  
GENERAL BUILDING CONSTRUCTION  
( *First Revision* )

UDC 691.41—431



© *Copyright* 1982

INDIAN STANDARDS INSTITUTION  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

*Indian Standard*

SPECIFICATION FOR  
SOIL BASED BLOCKS USED IN  
GENERAL BUILDING CONSTRUCTION  
( *First Revision* )

Soil Engineering and Rock Mechanics Sectional Committee, BDC 23

*Chairman*

DR JAGDISH NARAIN

*Representing*

University of Roorkee, Roorkee

*Members*

ADDITIONAL DIRECTOR RESEARCH ( F. E. ), RDSO DEPUTY DIRECTOR RESEARCH ( SOIL MECH ) ( <i>Alternate</i> )	Ministry of Railways
SHRI P. D. AGARWAL	Public Works Department, Government of Uttar Pradesh, Lucknow
DR B. L. DHAWAN ( <i>Alternate</i> )	
PROF ALAM SINGH	University of Jodhpur, Jodhpur
COL AVTAR SINGH	Engineer-in-Chief's Branch, Army Headquarters
LT-COL V. K. KANITKAR ( <i>Alternate</i> )	
CHIEF ENGINEER ( D & R )	Irrigation Department, Government of Punjab
SHRI M. C. DANDAVATE	The Concrete Association of India, Bombay
SHRI N. C. DUGGAL ( <i>Alternate</i> )	
SHRI A. G. DASTIDAR	In personal capacity ( 5 <i>Hungerford Street, 12/1, Hungerford Court, Calcutta 700 017</i> )
DR G. S. DHILLON	Indian Geotechnical Society, New Delhi
DIRECTOR, IRI	Irrigation Department, Government of Uttar Pradesh, Roorkee
SHRI A. H. DIVANJI	Asia Foundations and Constructions ( P ) Ltd, Bombay
SHRI A. N. JANGLE ( <i>Alternate</i> )	
DR GOPAL RAJAN	Institution of Engineers ( India ), Calcutta; and University of Roorkee, Roorkee
SHRI S. GUPTA	Cemindia Co Ltd, Bombay
SHRI N. V. DE-SOUSA ( <i>Alternate</i> )	

( *Continued on page 2* )

© Copyright 1982

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* ( XIV of 1957 ) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

( Continued from page 1 )

<i>Members</i>	<i>Representing</i>
SHRI G. S. JAIN	G. S. Jain & Associates, Roorkee
SHRI VIJAY K. JAIN ( <i>Alternate</i> )	
SHRI A. B. JOSHI	Central Soil and Material Research Station, New Delhi
DEPUTY DIRECTOR ( CSMRS ) ( <i>Alternate</i> )	
COL M. V. KAYERKAR	Ministry of Defence ( R & D )
SHRI V. B. GHORPADE ( <i>Alternate</i> )	
SHRI O. P. MALHOTRA	Public Works Department, Chandigarh Adminis- tration, Chandigarh
SHRI D. R. NARAHARI	Central Building Research Institute ( CSIR ), Roorkee
SHRI B. G. RAO ( <i>Alternate</i> )	
SHRI T. K. NATRAJAN	Central Road Research Institute ( CSIR ), New Delhi
DR G. V. RAO	Indian Institute of Technology, New Delhi
DR K. K. GUPTA ( <i>Alternate</i> )	
RESEARCH OFFICER ( B&RRL )	Public Works Department, Government of Punjab
SHRI K. R. SAXENA	Engineering Research Laboratories, Government of Andhra Pradesh, Hyderabad
SECRETARY	Central Board of Irrigation & Power, New Delhi
DY SECRETARY ( <i>Alternate</i> )	
SHRI N. SIVAGURU	Roads Wing ( Ministry of Shipping and Transport )
SHRI D. V. SIKKA ( <i>Alternate</i> )	
SHRI K. S. SRINIVASAN	National Buildings Organization, New Delhi
SHRI SUNIL BERRY ( <i>Alternate</i> )	
SHRI N. SUBRAMANYAM	Karnataka Engineering Research Station, Krishna- rajasagar
SUPERINTENDING ENGINEER	Public Works Department, Government of Tamil ( P & D ) Nadu, Madras
EXECUTIVE ENGINEER	
( SMRD ) ( <i>Alternate</i> )	
SHRI G. RAMAN, Director ( Civ Engg )	Director General, ISI ( <i>Ex-officio Member</i> )

*Secretary*

SHRI K. M. MATHUR  
Deputy Director ( Civ Engg ), ISI

Soil Testing Procedures and Equipment Subcommittee, BDC 23:3

*Convener*

DR ALAM SINGH                      University of Jodhpur, Jodhpur

*Members*

SHRI AMAR SINGH                      Central Building Research Institute ( CSIR ),  
Roorkee  
SHRI M. R. SONEJA ( *Alternate* )

( Continued on page 7 )

*Indian Standard*  
SPECIFICATION FOR  
SOIL BASED BLOCKS USED IN  
GENERAL BUILDING CONSTRUCTION  
( *First Revision* )

0. FOREWORD

**0.1** This Indian Standard ( First Revision ) was adopted by the Indian Standards Institution on 14 April 1982, after the draft finalized by the Soil Engineering and Rock Mechanics Sectional Committee had been approved by the Civil Engineering Division Council.

**0.2** Development during the last two decades in the use of soil based blocks in different parts of the world and the experience which has been gained for nearly a decade in the field of construction in India hold out a great promise for the use of soil based blocks in general building construction, particularly in low-cost structures. Experience shows that most soils can be satisfactorily stabilized with cement-lime. It is, however, necessary to conduct comprehensive tests on soils in a laboratory in order to determine the optimum requirements to give the specified properties. While in general building construction soil based blocks may be used as a substitute for bricks, their use should be avoided in the case of isolated load bearing columns, piers and such other heavily loaded structures.

**0.2.1** This standard was first published in 1960. Based on further studies conducted, this revision has been prepared. The principal modification is in respect of weathering test, which has been prescribed as per studies conducted at Indian Institute of Science, Bangalore. The revision now covers all types of soil based blocks.

**0.3** For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS:2-1960\*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

---

\*Rules for rounding off numerical values ( *revised* ).

**1. SCOPE**

**1.1** This standard covers the requirements and test for soil based blocks for use in general building construction.

**2. GENERAL**

**2.1** Soil based blocks shall be manufactured from a mixture of suitable soil and ordinarily portland cement or lime pozzolana mixture thoroughly mixed together, preferably in a mechanical mixer. The mixture is moulded and cast into blocks.

**3. CLASSIFICATION**

**3.1** The blocks shall be of two classes, Class 20 and Class 35 (*see 5.1*).

**4. SIZES**

**4.1** There shall be three sizes of soil-cement blocks, the dimensions of which shall be as follows:

<i>Length</i>	<i>Breadth</i>	<i>Height</i>
cm	cm	cm
19	9	9
19	9	4
29	19	9

**4.2** The dimensions shall be tested in accordance with the procedure given in **4.2.1** and shall be within following limits per twenty blocks.

<i>Block Size</i>	<i>Length</i>	<i>Breadth</i>	<i>Height</i>
cm	cm	cm	cm
19 × 9 × 9	372 to 388	174 to 186	174 to 186
19 × 9 × 4	372 to 388	174 to 186	74 to 86
29 × 19 × 9	570 to 590	372 to 388	174 to 186

**4.2.1** Twenty ( more according to the size of stack ) whole blocks shall be selected at random from the sample selected under **6**. All blisters, loose particles of clay and small projections shall be removed. They shall then be arranged upon a level surface successively in contact with each other and in a straight line. The overall length of the assembled blocks shall be measured with a steel tape or other suitable inextensible measures sufficiently long to measure the whole row at one stretch. Measurement by repeated application of short rule or measure shall not be permitted. If, for any reason, it is found impracticable to measure blocks in one row, the

sample may be divided into rows of 10 blocks each, which shall be measured separately to the nearest millimetre. All these dimensions shall be added together.

4.3 Each block shall also have a frog one centimetre deep and  $10 \times 4$  cm on one of its flat sides.

## 5. PHYSICAL REQUIREMENTS

5.1 **Compressive Strength** — The blocks when tested in accordance with the procedure laid down in IS: 3495 ( Part I )-1976\* shall have a minimum average compressive strength of not less than  $20 \text{ kgf/cm}^2$  for Class 20 and  $30 \text{ kgf/cm}^2$  for Class 30.

5.1.1 The compressive strength of any individual block shall not fall below the minimum average compressive strength by more than 20 percent.

5.2 **Water Absorption** — The block when tested in accordance with the procedure laid down in IS: 3495 ( Part II )-1976†, after immersion in cold water for 24 hours, an average water absorption shall not be more than 15 percent by weight.

5.3 **Weathering** — When tested in accordance with Appendix A, the maximum loss of weight shall not exceed 5 percent.

## 6. SAMPLING AND CRITERIA FOR CONFORMITY

6.1 Sampling and criteria for conformity of the blocks shall be done in accordance with the procedure laid down in IS: 5454-1978‡.

## 7. MARKING

7.1 Each block shall be marked in the frog with the manufacturer's identification mark or initials.

7.1.1 The manufacturers may also use the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution ( Certification Marks ) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

\*Methods of test for burnt clay building bricks: Part I Determination and compressive strength ( *second revision* ).

†Methods of test for burnt clay building bricks: Part II Determination of water absorption ( *second revision* ).

‡Methods for sampling of clay building bricks ( *first revision* ).

## APPENDIX A

( Clause 5.3 )

### WEATHERING TEST

**A-1. PRINCIPLE** The parameters that need be simulated in the weathering test are the ( i ) rain drop diameter at impact ( range in 2 mm for medium intensity and 4 mm for high intensity ) ( ii ) maximum terminal velocity of 6.5 m/sec at impact, and ( iii ) maximum intensity of rainfall, 15-30 mm/hr.

#### A-2. TEST SPECIMENS

**A-2.1** Three whole blocks shall be selected from the sample of blocks produced after carrying out the test for dimensional conformity. These blocks shall be designated as specimen A, B and C respectively.

#### A-3. SPRAY TEST

**A-3.1** A set of spray non-rustable showers that can produce a hard spray all over the block should be used. The diameter of each shower is 10 cm with 36 holes of 2 mm diameter. A facility for providing a device pump to create a constant pressure of  $1.5 \pm 0.2 \text{ kgf/cm}^2$  should be available for this test.

#### A-4. PROCEDURE

**A-4.1** The block to be tested is to be mounted on a test rig, such that only one face is exposed to shower and discharged water should find an exit without wetting the other faces or getting collected such that blocks get immersed. These showers are placed at a distance of 18 cm from the block and are arranged by the side, such that the complete face gets exposed. The period of exposure is limited to 2 hours and then the exposed surfaces are examined for possible pitting. The tests are carried out on at least 3 blocks. The limiting diameter of the pit formed is to be within 1 cm for passing this weathering test.

( Continued from page 2 )

<i>Members</i>	<i>Representing</i>
COL AVTAR SINGH	Ministry of Defence
LT COL V. K. KANITKAR ( <i>Alternate</i> )	
DIRECTOR ( CSMRS )	Central Soil and Material Research Station, New Delhi
DEPUTY DIRECTOR ( CSMRS ) ( <i>Alternate</i> )	
DIRECTOR ( PWDRI )	Public Works Department, Government of UP, Lucknow
DR B. L. DHAWAN ( <i>Alternate</i> )	
DEPUTY DIRECTOR RESEARCH ( FE-II ), RDSO	Ministry of Railways
DEPUTY DIRECTOR RESEARCH ( SM )-III, RDSO ( <i>Alternate</i> )	
PROF GOPAL RANJAN	University of Roorkee, Roorkee
DR S. C. HANDA ( <i>Alternate</i> )	
SHRI H. K. GUHA	Geologists Syndicate Pvt Ltd, Calcutta
SHRI N. N. BHATTACHARAYA ( <i>Alternate</i> )	
DR SUSHIL K. GULHATI	Indian Institute of Technology, New Delhi
SHRI P. JAGANATHA RAO	Central Road Research Institute (CSRI), New Delhi
SHRI M. D. NAIR	Associated Instruments Mfrs ( I ) Pvt Ltd, New Delhi
PROF T. S. NAGARAJ ( <i>Alternate</i> )	
SHRI N. M. PATEL	Delhi College of Engineering, Delhi
RESEARCH OFFICER ( B & RRL )	Public Works Department, Government of Punjab



## INTERNATIONAL SYSTEM OF UNITS ( SI UNITS )

### Base Units

<i>Quantity</i>	<i>Unit</i>	<i>Symbol</i>
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

### Supplementary Units

<i>Quantity</i>	<i>Unit</i>	<i>Symbol</i>
Plane angle	radian	rad
Solid angle	steradian	sr

### Derived Units

<i>Quantity</i>	<i>Unit</i>	<i>Symbol</i>	<i>Definition</i>
Force	newton	N	1 N=1kg. m/s <sup>2</sup>
Energy	joule	J	1 J=1 N.m
Power	watt	W	1 W=1 J/s
Flux	weber	Wb	1 Wb=1 V.s
Flux density	tesla	T	1 T=1 Wb/m <sup>2</sup>
Frequency	hertz	Hz	1 Hz=1 c/s (s <sup>-1</sup> )
Electric conductance	siemens	S	1 S=1 A/V
Electromotive force	volt	V	1 V=1 W/A
Pressure, stress	pascal	Pa	1 Pa=1 N/m <sup>2</sup>

# PUBLICATIONS OF INDIAN STANDARDS INSTITUTION

## INDIAN STANDARDS

Over 10 000 Indian Standards covering various subjects have been issued so far. Of these, the standards belonging to the Civil Engineering Group fall under the following categories:

Aggregates, concrete	Modular co-ordination
Apparatus for testing cement and concrete	Multi-purpose river valley projects
Asbestos cement products	Pipes
Bricks and blocks	Planning, regulation and control
Builder's hardware	Plaster, paint and allied finishes
Cement	Plywood and allied products
Concrete design and construction	Poles
Concrete testing	Pozzolanas
Construction equipment	Reinforcement, concrete
Construction practices	Roof and roof coverings
Doors and windows	Safety in construction
Drawing office practice and equipment	Sieves and wire gauzes
Fire fighting equipment	Soil engineering
Fire safety	Stones, building
Flexible floor coverings	Structural design
Floor finishes	Tar and bitumen
Fluid flow measurement	Tiles
Fluid flow measuring instruments	Timber
Foundation engineering	Timber design and construction
Functional design of buildings	Timber stores
Furniture	Wall and ceiling finish
Gypsum products	Waterproofing and damp-proofing
Lime, building	Water supply, drainage and sanitation
Loading standards, structural safety	Water supply, sanitation and drainage fittings
Measurement and estimation of civil engineering	Wood-based materials
	Unclassified

### OTHER PUBLICATIONS

ISI Bulletin ( Published Every Month )						
Single Copy	...	...	...	...	...	Rs 4-00
Annual Subscription	...	...	...	...	...	Rs 36-00
Standards: Monthly Additions						
Single Copy	...	...	...	...	...	Rs 0-30
Annual Subscription	...	...	...	...	...	Rs 3-00
Annual Reports ( from 1948-49 Onwards )	...	...	...	...	...	Rs 2-00 to 7-00
ISI Handbook, 1980	...	...	...	...	...	Rs 100-00

### INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 26 60 21, 27 01 31

Telegrams : Manaksanstha

#### Regional Offices:

Western : Novelty Chambers, Grant Road  
 Eastern : 5 Chowringhee Approach  
 Southern : C.I.T. Campus  
 Northern : B69, Phase VII

	Telephone
BOMBAY 400007	37 97 29
CALCUTTA 700072	27 50 90
MADRAS 600113	41 24 42
S.A.S. NAGAR (MOHALI) 160051	—

#### Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur  
 'F' Block, Unity Bldg, Narasimharaja Square  
 Gangotri Complex, Bhadbhada Road, T.T. Nagar  
 22E Kalpana Area  
 5-8-56C L. N. Gupta Marg  
 R14 Yudhister Marg, C Scheme  
 117/418 B Sarvodaya Nagar  
 Patliputra Industrial Estate  
 Hantex Bldg ( 2nd Floor ), Rly Station Road

AHMADABAD 380001	2 03 91
BANGALORE 560002	22 48 05
BHOPAL 462003	6 27 16
BHUBANESHWAR 751014	5 36 27
HYDERABAD 500001	22 10 83
JAIPUR 302005	6 98 32
KANPUR 208005	4 72 92
PATNA 800013	6 28 08
TRIVANDRUM 695001	32 27