


Indian Standard

METHODS OF TEST FOR STABILIZED SOILS

**PART VII DETERMINATION OF CEMENT CONTENT OF
CEMENT STABILIZED SOILS**

UDC 624.138 : 543 : 666.94



© Copyright 1973

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110001

Price Rs 4.00

July 1973

Indian Standard

METHODS OF TEST FOR STABILIZED SOILS

PART VII DETERMINATION OF CEMENT CONTENT OF CEMENT STABILIZED SOILS

Soil Engineering Sectional Committee, BDC 23

<i>Chairman</i>	<i>Representing</i>
PROF DINESH MOHAN	Central Building Research Institute (CSIR), Roorkee
<i>Members</i>	
SHRI D. R. NARAHARI (<i>Alternate to</i> Prof Dinesh Mohan)	
PROF ALAM SINGH	University of Jodhpur, Jodhpur
DR A. BANERJEE	Cementation Co Ltd, Bombay
SHRI S. GUPTA (<i>Alternate</i>)	
SHRI B. B. L. BHATNAGAR	Irrigation and Power Research Institute, Amritsar
SHRI K. N. DADINA	In personal capacity (<i>P-820 New Alipore,</i> <i>Calcutta-53</i>)
SHRI A. C. DASTIDAR	Hindustan Construction Co, Bombay
SHRI R. L. DEWAN	Irrigation Research Institute, Khagaul, Patna
DR G. S. DHILLON	Indian Geotechnical Society, New Delhi
DIRECTOR (CSMRS)	Central Water & Power Commission, New Delhi
DEPUTY DIRECTOR (CSMRS) (<i>Alternate</i>)	
PROF R. N. DOGRA	Indian Institute of Technology, New Delhi
SHRI S. K. GULHATI (<i>Alternate</i>)	
DR IQBAL ALI	Engineering Research Laboratories, Hyderabad
SHRI K. R. SAXENA (<i>Alternate</i>)	
JOINT DIRECTOR RESEARCH (FE), RDSO	Railway Board (Ministry of Railways)
DEPUTY DIRECTOR RESEARCH (SOIL MECHANICS), RDSO (<i>Alternate</i>)	
SHRI G. KUECKELMANN	Radio Foundation Engineering Ltd; and Hazarat & Co, Bombay
SHRI A. H. DIVANJI (<i>Alternate</i>)	
SHRI O. P. MALHOTRA	Public Works Department, Government of Punjab
SHRI M. A. MEHTA	Concrete Association of India, Bombay
SHRI T. M. MENON (<i>Alternate</i>)	
SHRI T. K. NATARAJAN	Central Road Research Institute (CSIR), New Delhi

(Continued on page 2)

© Copyright 1973

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 4332 (Part VII) - 1973

(Continued from page 1)

Members	Representing
SHRI RAVINDER LAL	National Buildings Organization, New Delhi
SHRI S. H. BALACHANDANI (Alternate)	
RESEARCH OFFICER	Buildings & Roads Research Laboratory, Public Works Department, Government of Punjab
MAJ K. M. S. SAHASI	Engineer-in-Chief's Branch, Army Headquarters
SHRI P. PUTHISIGAMANI (Alternate)	
SECRETARY	Central Board of Irrigation & Power, New Delhi
DR SHAMSHER PRAKASH	University of Roorkee, Roorkee
SHRI H. D. SHARMA	Irrigation Research Institute, Roorkee
SHRI S. N. SINHA	Roads Wing (Ministry of Shipping & Transport)
SHRI A. S. BISHNOI (Alternate)	
SUPERINTENDING ENGINEER (PLANNING AND DESIGN CIRCLE)	Concrete & Soil Research Laboratory, Public Works Department, Government of Tamil Nadu
EXECUTIVE ENGINEER-IN-CHARGE (SOIL MECHANICS AND RESEARCH DIVISION) (Alternate)	
SHRI C. G. SWAMINATHAN	Institution of Engineers (India), Calcutta
SHRI H. C. VERMA	All India Instruments Manufacturers & Dealers Association, Bombay
SHRI V. K. VASUDEVAN (Alternate)	
SHRI H. G. VERMA	Public Works Department, Government of Uttar Pradesh
SHRI D. C. CHATURVEDI (Alternate)	
SHRI D. AJITHA SIMHA, Director (Civ Engg)	Director General, ISI (Ex-officio Member)

Secretary

SHRI G. RAMAN
Deputy Director (Civ Engg), ISI

Soil Testing Procedures and Equipment Subcommittee, BDC 23 : 3

Convener

PROF ALAM SINGH
University of Jodhpur, Jodhpur

Members

DR R. K. BHANDARI	Central Road Research Institute (CSIR), New Delhi
SHRI T. N. BHARGAVA	Roads Wing (Ministry of Shipping & Transport)
SHRI A. S. BISHNOI (Alternate)	
DR ASIT KUMAR CHATTERJEE	Public Works Department, Government of Uttar Pradesh
SHRI R. L. DEWAN	Irrigation Research Institute, Khagaul, Patna
DIRECTOR (CSMRS)	Central Water & Power Commission, New Delhi
DEPUTY DIRECTOR (CSMRS) (Alternate)	
SHRI N. K. GUHA	Geologists' Syndicate Private Ltd, Calcutta
SHRI N. N. BHATTACHARAYA (Alternate)	

(Continued on page 9)

Indian Standard

METHODS OF TEST FOR STABILIZED SOILS

PART VII DETERMINATION OF CEMENT CONTENT OF CEMENT STABILIZED SOILS

0. F O R E W O R D

0.1 This Indian Standard (Part VII) was adopted by the Indian Standards Institution on 16 February 1973, after the draft finalized by the Soil Engineering Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Soil stabilization is the chemical or mechanical treatment designed to increase or maintain the stability of mass of soil or otherwise to improve its engineering properties. There are several methods of stabilization and these may be broadly classified on the basis of treatment given to the soil (for example, dewatering and compaction), process involved (for example, thermal and electrical), and additives employed (for example, asphalt and cement). The choice of a particular method depends on the characteristics of the problem on hand and on the nature of soil type encountered. For studying in the laboratory, the methods and effects of stabilization, certain standard methods of test for the evaluation of properties of stabilized soils and their analysis are required. The required standards on methods of test for stabilized soils are being published in parts and this part lays down the method of test for determining cement content of cement stabilized soils.

0.3 In the formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country. This has been met by basing the standard on the following publications:

ASTM : D806-1965 Method of test for cement content of soil-cement mixtures. American Society for Testing and Materials.

DEWAN (RL). The rapid estimation of cement content in mortar and concrete. Indian Concrete Journal. April 1959.

IS : 4332 (Part VII) - 1973

0.4 In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960*.

1. SCOPE

1.1 This standard (Part VII) lays down the method of test for determining cement content of cement stabilized soils.

2. APPARATUS

2.1 **Analytical Balance** — sensitive to 0.001 g.

2.2 **Glass Beakers** — three of 250-ml capacity and two of 600-ml capacity.

2.3 **Glass Funnel** — 6 cm diameter.

2.4 **Burette** — one, 50 ml.

2.5 **Pipette** — 25 ml.

2.6 **Conical Flasks** — two of 250-ml capacity.

2.7 **Filter Papers** — Whatman No. 41 and 42 or equivalent.

2.8 **Heating Equipment**

2.9 **Drying Oven**

2.10 **Sieves** — 40-mm, 20-mm, 10-mm, 4.75-mm and 425-micron IS Sieves conforming to the requirements of IS : 460-1962†.

3. REAGENTS

3.0 **Quality of Reagents** — Unless specified otherwise, pure chemicals and distilled water (see IS : 1070-1960‡) shall be used in tests.

NOTE — ' Pure chemicals ' shall mean chemicals that do not contain impurities which affect the results of analysis.

3.1 **Potassium Permanganate Solution** — N/10; dissolve 3.2 to 3.25 g of potassium permanganate on a watch-glass and dissolve in one litre of distilled water. Heat the solution to boiling, and allow the solution to cool to room temperature. Filter the solution through a funnel containing a plug of purified glass wool. The solution should be stored in a glass stoppered bottle and kept in dark and its exact normality ascertained with standard oxalic acid solution.

*Rules for rounding off numerical values (revised).

†Specification for test sieves (revised).

‡Specification for water, distilled quality (revised).

3.2 Oxalic Acid — N/10; weigh 1.575 g of $\text{H}_2\text{C}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$ and make up to 250 ml in a volumetric flask.

3.3 Sulphuric Acid — 2 N; add 12.5 ml of pure sulphuric acid to 240 ml of water.

3.4 Ammonium Nitrate — Dissolve 20 g of ammonium nitrate in one litre of water.

3.5 Hydrochloric Acid — 2 N; sp gr 1.19 mixed with equal volume of distilled water.

3.6 Ammonium Oxalate — saturated solution.

3.7 Ammonium Hydroxide — sp gr 0.89. Mix ammonium hydroxide and distilled water in the ratio of 1 : 2 (one part of ammonia and two parts of distilled water).

3.8 Calcium Chloride Solution — Dissolve one part by weight of salt in 100 parts by weight of distilled water.

4. SAMPLES

4.0 Samples given in 4.1 to 4.3 shall be selected for the test as given in IS : 4332 (Part I)-1967*.

4.1 Raw Soil — representative of the soil phase of the soil-cement mixture.

NOTE — The results of this test are very sensitive to the variation of calcium content in soil. Hence, due attention should be paid to sampling to obtain representative samples and the number of samples to be tested.

4.2 Cement — representative of the cement phase of the soil-cement mixture.

4.3 Soil-Cement — representative sample of the mixture to be analyzed.

5. PROCEDURE

5.1 Dry 25 g of each sample in the drying oven at $110 \pm 5^\circ\text{C}$ to a constant weight. Pulverize the samples to pass through a 425-micron IS Sieve.

5.2 Weigh out separately on analytical balance raw soil, 5 g; soil-cement mixture, 5 g; and cement, 1 g. Transfer each of the weighed samples to separate 250-ml beakers. Add 50 ml of hydrochloric acid (2N), to each sample. Cover it and boil gently on a hot-plate for 5 min.

*Methods of test for stabilized soils; Part I Sampling and preparation of stabilized soils for testing.

5.3 To each of the beakers add 25 ml of hot distilled water and filter the contents through Whatman No. 42 filter paper and receive each filtrate in a 250-ml volumetric flask separately. The material on the filter should be washed with small amounts of hot water repeatedly till free from chloride ions (about 4 times) (check with silver nitrate solution).

5.3.1 Take a small quantity of filtrate (say 1 cc) obtained from the soil-cement mixture treated by hydrochloric acid and add 3 cc of ammonium molybdate reagent and a few drops of concentrated nitric acid and warm to 40°C. A yellow precipitate indicates the presence of phosphate ions.

5.4 After completion of washing, discard the filter paper and dilute the filtrate in the volumetric flask to 250 ml with cold water. Shake the contents well and remove a 50-ml aliquot and transfer to the original 250-ml beaker (see 5.2), using 250-ml pipette. Dilute to 100 ml. Add a few millilitres of bromine water or a few drops of concentrated nitric acid. Boil, cool and make the solution slightly ammoniacal with ammonium hydroxide. Boil for two minutes and allow the hydroxide to settle.

5.4.1 In case of soil-cement mixture containing phosphate, dissolve the precipitates of hydroxides in the minimum quantity of dilute hydrochloric acid. To the main solution, add dilute ammonia solution drop by drop with stirring, until either a faint permanent precipitate is just obtained or the solution is just alkaline. Then add 2 to 3 ml of dilute acetic acid (1 : 1) and 10 ml of 3N ammonium acetate solution. Discard any precipitate, which may form at this stage. If the solution is red, sufficient ferric ion is present in the solution combined with all the phosphate ions. If the solution is not red in colour, add neutral ferric chloride (FeCl_3) solution, drop by drop and with stirring until the solution acquires a deep brownish red colour. Dilute the solution to 150 ml with hot water, boil gently, filter hot and wash the residue with a little boiling water. The residue will contain the phosphates of Fe, Al and Cr and may be discarded. Boil down the filtrate to 20 to 25 cc and proceed as given in 5.6.

5.5 Filter hydroxides except soil-cement mixture containing phosphates for which the process of separation has been given in 5.4.1 through Whatman No. 41 filter paper, receiving filtrate in a 600-ml beaker. Wash the original 250-ml beaker into the filter once with a stream of ammonium nitrate and then with hot ammonium nitrate twice. Set aside the filtrate and place original beaker under funnel. Perforate the paper with a rod and wash the hydroxides into the original beaker with hot ammonium nitrate to remove most of the precipitate from the filter paper. Treat the paper with 2 ml of hot hydrochloric acid (1 : 3). Wash the paper

several times with hot water, and then discard the paper. Dilute the solution to 75 ml.

5.6 Make the solution slightly ammoniacal with constant stirring and boil for 1 to 2 minutes. Allow the precipitate to settle and filter through Whatman No. 41 filter paper. Receive the filtrate in 600-ml beaker (see 5.5). Wash the precipitate with ammonium nitrate three to four times. Discard the hydroxide precipitate. Add 2 to 3 drops of methyl red indicator and ammonium hydroxide (sp gr 0.89) to the filtrate till the colour changes from faint pink to yellow ($pH = 5$, optimum for calcium oxalate precipitation). Heat the solution to boiling and add 10 ml of hot saturated ammonium oxalate solution. Keep the mixture near boiling until the precipitate becomes 'granular', then set aside on a warm hot-plate for 30 min or more. Check the completeness of precipitation. Filter off calcium oxalate precipitate through Whatman No. 42. Clean the beaker with rubber policeman and transfer the contents to the filter with a stream of hot water. Wash the filter 8 to 10 times with hot water or preferably four times each with ammonium hydroxide (2 : 98) to make sure that soluble oxalates are completely removed. This can be checked with calcium chloride solution.

NOTE — Calcium content in the soil, cement and soil-cement mixture may also be determined by rapid method given below:

Filter the acid solution (see 5.4), wash and make up to 100 ml of which 50 ml are just neutralized with liquid ammonia. Dissolve the precipitates of aluminium oxide and ferric oxide thus formed by just the quantity of glacial acetic acid required for dissolving the precipitates. Then add in excess saturated solution of ammonium oxalate to the solution to form a copious precipitate of calcium oxalate. Filter off calcium oxalate precipitate, wash with hot water till free from oxalates. Dissolve the oxalates in (1 : 4) sulphuric acid and titrate with standard potassium permanganate solution to determine the percentage of calcium.

5.7 Open the filter paper carefully and wash the precipitate into the beaker in which the precipitation was affected. Dilute to 200 ml and add 10 ml of sulphuric acid (1 : 1).

5.8 Heat the aliquot portion (5.7) to 65°C on a water-bath maintained at 60 to 65°C and titrate it with standard potassium permanganate solution to a persistent pink colour for 10 seconds. Take two more readings. Five times the average value is the reading P as in 6.1.

5.9 Blank — Make a blank determination, following the same procedure using same amount of reagents.

6. CALCULATIONS

6.0 Cement Content of the Soil — Cement mixture should be calculated as given in 6.1 and 6.2.

6.1 Calculate the percentages of calcium oxide in the soil, the cement, and the soil-cement mixture as follows:

$$\text{Percentage of calcium oxide} = \frac{(P - Q) R \times 0.028}{S} \times 100$$

where

P = ml of potassium permanganate solution required for titration of the sample;

Q = ml of potassium permanganate solution required for titration of the blank;

R = normality of the potassium permanganate solution = 0.1;

S = weight of sample represented by the aliquot titrated, in g; and

0.028 = calcium oxide equivalent of 1 ml of 1 N potassium permanganate.

6.2 Calculate the percentage by weight of cement in the soil-cement mixture as follows:

$$\text{Percentage cement} = \frac{(X - Y)}{Z} \times 100$$

where

X = percentage of calcium oxide in soil-cement mixture,

Y = percentage of calcium oxide in raw soil, and

Z = percentage of calcium oxide in cement.

NOTE — When hydrated soil-cement mixtures (that is, mixtures prepared and laid sometime earlier) are analyzed, the value of percentage by weight of cement obtained is in terms of hydrated cement. Such values need to be converted to an approximate equivalent of dry cement, through a factor which is of the order of 1.04.

(Continued from page 2)

Members

SHRI S. K. GULHATI
SHRI O. P. MALHOTRA
SHRI D. R. NARAHARI

SHRI G. S. JAIN (*Alternate*)
DR V. V. S. RAO
SHRI K. K. GUPTA (*Alternate*)
MAJ K. M. S. SAHASI
PROF R. B. SINGH
SHRI H. C. VERMA

SHRI M. N. BALIGA (*Alternate*)

Representing

Indian Institute of Technology, New Delhi
Public Works Department, Government of Punjab
Central Building Research Institute (CSIR),
Roorkee

United Technical Consultants Pvt Ltd, New Delhi

Engineer-in-Chief's Branch, Army Headquarters
Banaras Hindu University, Banaras
Associated Instrument Manufacturers (India)
Pvt Ltd, New Delhi

INDIAN STANDARDS

ON

METHODS OF TEST FOR SOILS

IS:

2720 Methods of test for soils:

- (Part I)-1972 Preparation of dry soil samples for various tests (*first revision*)
- (Part II)-1969 Determination of moisture content (*first revision*)
- (Part III)-1964 Determination of specific gravity
- (Part IV)-1965 Grain size analysis
- (Part V)-1970 Determination of liquid and plastic limits (*first revision*)
- (Part VI)-1972 Determination of shrinkage factors (*first revision*)
- (Part VII)-1965 Determination of moisture content-dry density relation using light compaction
- (Part VIII)-1965 Determination of moisture content-dry density relation using heavy compaction
- (Part IX)-1971 Determination of dry density-moisture content relation by constant weight of soil method
- (Part X)-1964 Determination of unconfined compressive strength
- (Part XI)-1971 Determination of shear strength parameters of a specimen tested in unconsolidated undrained triaxial compression without the measurement of pore water pressure
- (Part XIII)-1972 Direct shear test (*first revision*)
- (Part XIV)-1968 Determination of density index (relative density) of cohesionless soils
- (Part XV)-1965 Determination of consolidation properties
- (Part XVI)-1965 Laboratory determination of CBR
- (Part XVII)-1966 Laboratory determination of permeability
- (Part XVIII)-1964 Determination of field moisture equivalent
- (Part XIX)-1964 Determination of centrifuge moisture equivalent
- (Part XX)-1966 Determination of linear shrinkage
- (Part XXI)-1965 Determination of total soluble solids
- (Part XXII)-1972 Determination of organic matter (*first revision*)
- (Part XXIII)-1966 Determination of calcium carbonate
- (Part XXIV)-1967 Determination of base exchange capacity
- (Part XXV)-1967 Determination of silica sesquioxide ratio
- (Part XXVI)-1967 Determination of pH value
- (Part XXVII)-1968 Determination of total soluble sulphates
- (Part XXVIII)-1966 Determination of dry density of soils, in-place, by the sand replacement method
- (Part XXIX)-1966 Determination of dry density of soils in-place by the core-cutter method
- (Part XXX)-1968 Laboratory vane shear test for soils
- (Part XXXI)-1969 Field determination of CBR
- (Part XXXII)-1970 North dakota cone test
- (Part XXXIII)-1971 Determination of the density in-place by the ring and water replacement method
- (Part XXXIV)-1971 Determination of density of soil in-place by rubber-balloon method

AMENDMENT NO. 1 APRIL 1983

TO

IS:4332(PART VII)-1973 METHODS OF TEST FOR STABILIZED SOILS
PART VII DETERMINATION OF CEMENT CONTENT OF CEMENT STABILIZED
SOILS

Alterations

(Page 4, clause 2.10, line 2) - Substitute 'IS:460(Part I)-1978[†]' for
'IS:460 1962[†]'

(Page 4, clause 3.0, line 2) - Substitute 'IS:1070-1977[‡]' for
'IS:1070-1960[‡]'

(Page 4, foot-notes with '†' and '‡' marks) - Substitute the following
for the existing:

[†]Specification for test sieves: Part I Wire cloth test sieves
(second revision).

[‡]Specification for water for general laboratory use (second revision).