

IS : 4845 - 1968

Indian Standard
DEFINITIONS AND TERMINOLOGY
RELATING TO HYDRAULIC CEMENT

(Fourth Reprint SEPTEMBER 1994)

UDC 001.4:666.94

© *Copyright* 1969

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Gr 2

March 1969

*Indian Standard*DEFINITIONS AND TERMINOLOGY
RELATING TO HYDRAULIC CEMENT

Cement and Concrete Sectional Committee, BDC 2

Chairman

SHRI J. DATT

Representing

The Concrete Association of India, Bombay

*Members*SHRI M. A. MEHTA (*Alternate to*
Shri J. Datt)SHRI A. P. BAGCHI
SHRI P. S. BHATNAGAR
DR S. K. CHOPRASahu Cement Service, New Delhi
Bhakra & Beas Designs Organization, New Delhi
Central Building Research Institute (CSIR),
RoorkeeSHRI J. S. SHARMA (*Alternate*)

DIRECTOR (CSM)

Central Water & Power Commission, New Delhi

DIRECTOR (DAMS III) (*Alternate*)

DR R. K. GHOSH

Indian Roads Congress, New Delhi

DR R. R. HATTIANGADI

The Associated Cement Companies Ltd, Bombay

SHRI V. N. PAI (*Alternate*)JOINT DIRECTOR STANDARDS
(B & S)Research, Designs & Standards Organization
(Ministry of Railways), LucknowDEPUTY DIRECTOR STANDARDS
(B & S) (*Alternate*)

SHRI S. B. JOSHI

S. B. Joshi & Co Ltd, Bombay

PROF S. R. MEHRA

Central Road Research Institute (CSIR), New
DelhiDR R. K. GHOSH (*Alternate*)

DR S. N. MUKERJI

National Test House, Calcutta

SHRI E. K. RAMACHANDRAN (*Alternate*)

SHRI ERACH A. NADIRSHAH

Institute of Engineers (India), Calcutta

SHRI K. K. NAMBIAR

In personal capacity (16 First Crescent, Park Road,
Madras 20)

SHRI M. L. NANDA

Central Public Works Department

SUPERINTENDING ENGINEER,
2ND CIRCLE (*Alternate*)

BRIG NARESH PRASAD

Engineer-in-Chief's Branch, Army Headquarters

SO 1 DESIGN (PAVEMENT) (*Alternate*)

SHRI I. L. PATEL

Directorate General of Supplies & Disposals
(Ministry of Works, Housing & Supply)

SHRI RABINDER SINGH

National Buildings Organization (Ministry of Works,
Housing & Supply)SHRI B. D. AHUJA (*Alternate*)*(Continued on page 2)*BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
PROF G. S. RAMASWAMY	Structural Engineering Research Centre (CSIR), Roorkee
DR N. S. BEHAL (<i>Alternate</i>)	
SHRI T. N. S. RAO	Gammon India Ltd, Bombay
SHRI S. R. PINHEIRO (<i>Alternate</i>)	
REPRESENTATIVE	Geological Survey of India, Calcutta
REPRESENTATIVE	M. N. Dastur & Co (Pvt) Ltd, Calcutta
REPRESENTATIVE	The India Cements Ltd, Madras
SHRI K. G. SALVI	Hindustan Housing Factory Ltd, New Delhi
SHRI C. L. KASLIWAL (<i>Alternate</i>)	
SECRETARY	Central Board of Irrigation & Power, New Delhi
SHRI S. N. SINHA	Roads Wing, Ministry of Transport
SHRI KARTIK PRASAD (<i>Alternate</i>)	
SHRI L. SWAROOP	Dalmia Cement (Bharat) Ltd, New Delhi
SHRI A. V. RAMANA (<i>Alternate</i>)	
DR H. C. VISVEVARAYA	Cement Research Institute of India, New Delhi
SHRI R. NAGARAJAN, Director (Civ Engg)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI Y. R. TANEJA
Deputy Director (Civ Engg), ISI

Cement Subcommittee, BDC 2 : 1

Convener

DR R. R. HATTIANGADI The Associated Cement Companies Ltd, Bombay

Members

SHRI V. N. PAI (<i>Alternate to</i> Dr R. R. Hattiangadi)	
DR S. K. CHOPRA	Central Building Research Institute (CSIR), Roorkee
SHRI C. A. TANEJA (<i>Alternate</i>)	
SHRI J. DATT	The Concrete Association of India, Bombay
SHRI M. A. MEHTA (<i>Alternate</i>)	
DIRECTOR (CSM)	Central Water & Power Commission
JOINT DIRECTOR RESEARCH (B & S)	Research, Designs & Standards Organization (Ministry of Railways)
ASSISTANT DIRECTOR RESEARCH (B & S) (<i>Alternate</i>)	
SHRI M. GANGULI	Central Warehousing Corporation, New Delhi
SHRI R. K. GATTANI	Shree Digvijay Cement Co Ltd, Sikka
DR R. K. GHOSH	Central Road Research Institute (CSIR), New Delhi
SHRI R. M. KRISHNAN	National Metallurgical Laboratory (CSIR), Jamshedpur
SHRI R. L. KUMAR	Hindustan Steel Ltd, Ranchi
SHRI P. GON (<i>Alternate</i>)	

(Continued on page 7)

Indian Standard

DEFINITIONS AND TERMINOLOGY RELATING TO HYDRAULIC CEMENT

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 18 September 1968, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Hydraulic cement, more commonly known as cement, is one of the most extensively used basic materials in all civil engineering constructions. Tremendous progress in the civil engineering industry and the exacting demands of engineers for high quality building materials have resulted in the development of a large variety of hydraulic cements, both for specialized and general use in civil engineering constructions. There are a number of technical terms connected with the production and use of different type of hydraulic cements, which quite often require clarifications to give precise meaning to the stipulations in the standard specifications and other technical documents. This standard has been prepared with the object of defining various terms relating to hydraulic cements.

0.3 In the formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country.

0.4 This standard is one of a series of Indian Standards on cements. Other standards published in the series are the following:

*IS : 269-1967 Ordinary, rapid-hardening and low heat portland cement (*second revision*)

*IS : 455-1967 Portland blastfurnace slag cement (*second revision*)

*IS : 1489-1967 Portland-pozzolana cement (*first revision*)

IS : 650-1966 Standard sand for testing of cement (*first revision*)

IS : 4031-1968 Methods of physical tests for hydraulic cement

IS : 4032-1968 Methods of chemical analysis of hydraulic cement

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960†. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Since revised.

†Rules for rounding off numerical values (*revised*).

1. SCOPE

1.1 This standard lays down the general definitions applicable to hydraulic cements, as well as the particular definitions and the denominations which pertain to each type of cement.

2. GENERAL DEFINITIONS

2.1 Hydraulic Cement — Finely ground material which on addition of requisite quantity of water is capable of hardening both under water and in air by the chemical interaction of its constituents with water, and is also capable of bending together appropriate materials.

2.2 Component Materials

2.2.1 Principal Component Materials — The principal materials used in the manufacture of hydraulic cement should have either hydraulic or pozzolanic properties.

2.2.1.1 Hydraulic properties — Hydraulic properties are the ability of a material to set and harden in the presence of water, with formation of stable compounds.

2.2.1.2 Pozzolanic properties — The ability of a material to combine chemically with calcium hydroxide in the presence of water under ambient temperature forming compounds having cementitious properties.

2.2.2 Portland Clinker — Clinker, consisting mostly of calcium silicates, obtained by heating to incipient fusion a predetermined and homogeneous mixture of materials principally containing lime (CaO) and silica (SiO_2) with a smaller proportion of alumina (Al_2O_3) and iron oxide (Fe_2O_3).

2.2.3 Granulated Blastfurnace Slag — Blastfurnace slag in granulated form is used for the manufacture of hydraulic cement. Blastfurnace slag is non-metallic product consisting essentially of glass containing silicates and aluminosilicates of lime and other bases, which is developed simultaneously with iron in blastfurnace or electric pig iron furnace. Granulated slag is obtained by further processing the molten slag by rapidly chilling or quenching it with water or steam and air.

2.2.4 High Alumina Clinker — Clinker consisting mainly of mono calcium aluminates and obtained by complete or partial fusion of a predetermined mixture of materials mainly containing alumina (Al_2O_3) and lime (CaO) with smaller proportions of iron oxides, silica (SiO_2) and other oxides.

2.2.5 Pozzolana — An essentially silicious material which while in itself possessing little or no cementitious properties will, in finely divided form and in the presence of water, react with calcium hydroxide at ambient temperature to form compounds possessing cementitious properties. The

term includes natural volcanic material having pozzolanic properties as also other natural and artificial materials, such as diatomaceous earth, calcined clay and fly ash.

PORTLAND CEMENT

3.1 Portland Cement — Portland cement is the cement obtained by grinding Portland clinker with the possible addition of a small quantity of gypsum, water or both, and not more than one percent of air entraining agents or other agents which have proved not to be harmful (*see* IS : 269-1967*).

3.2 Additives — In the manufacture of Portland cement, any material, other than water or gypsum, or both, which is interground with the clinker, in an amount not to exceed one percent. The following two types of additives are recognized:

- a) Processing additives designed primarily to aid the cement manufacturer in grinding or otherwise processing or handling his cement, and
- b) Functional additives added primarily to modify the end properties of cement.

3.2.1 The additives should be covered by a statement of their nature completing the standard denomination of the cement.

3.3 Standard Denomination Portland Cements — Ordinary Portland cement, rapid hardening Portland cement and low-heat Portland cement.

4. CEMENT CONTAINING BLASTFURNACE SLAG

4.1 Portland Blastfurnace Slag Cement — An intimately interground mixture of Portland clinker and granulated blastfurnace slag with addition of gypsum and permitted additives (*see* 3.2) or an intimate and uniform blend of Portland cement and finely ground granulated blastfurnace slag (*see* IS : 455-1967†).

4.1.1 Standard Denomination — Portland blastfurnace slag cement. The abbreviation 'PBFS Cement' shall be used for 'Portland blastfurnace slag cement'.

4.2 Cements Composed Mainly of Blastfurnace Slag and Calcium Sulphate

4.2.1 Supersulphated Cement — A hydraulic cement having sulphuric anhydride (SO_3) content not more than 5 percent and made by

*Specification for ordinary, rapid-hardening and low heat Portland cement (*second revision*). (Since revised).

†Specification for Portland blastfurnace slag cement (*second revision*). (Since revised)

intergrinding a mixture of at least 70 percent granulated blastfurnace slag, calcium sulphate and a small amount of lime or Portland clinker.

4.2.2 Standard Denomination — Supersulphated cement.

5. HIGH ALUMINA CEMENT

5.1 High Alumina Cement — High alumina cement is the cement obtained by grinding high alumina clinker.

5.2 Standard Denomination — High alumina cement.

6. CEMENTS CONTAINING POZZOLANA

6.1 Cements containing pozzolana are cements obtained by intergrinding Portland clinker, gypsum and pozzolana or by intimate and uniform blending of Portland cement and fine pozzolana.

6.2 Portland-Pozzolana Cement — An intimately interground mixture of Portland clinker and pozzolana with the possible addition of gypsum or an intimate and uniform blend of Portland cement and fine pozzolana, the pozzolana constituent being within limits specified in IS: 1489-1967*.

6.2.1 Standard Denomination — Portland-pozzolana cement.

7. MASONRY CEMENT

7.1 Masonry Cement — Product obtained by intergrinding a mixture of Portland cement clinker with inert materials (non-pozzolanic), such as limestone, conglomerates, dolomite limestone and dolomite; and gypsum and an air entraining plasticiser, in suitable proportions so that the resulting product conforms to the requirements laid down in IS: 3466-1967†.

It is characterized by certain physical properties, such as slow-hardening, high workability and high water retentivity which make it especially suitable for masonry work.

7.2 Standard Denomination — Masonry cement.

8. OIL-WELL CEMENT

8.1 Hydraulic cement suitable for use in high pressure and temperature in sealing water and gas pockets and setting casings during the drilling and repair of oil-wells, often contains retarders to meet the requirements of such use in addition to coarser grinding and/or reduced tricalcium aluminate (C_3A) content of clinker.

*Specification for Portland-pozzolana cement (*first revision*). (Since revised).

†Specification for masonry cement.

9. SULPHATE-RESISTANT CEMENT

9.1 Sulphate-Resistant Portland Cement — Portland cement with its tricalcium aluminate (C_3A) content [calculated by the formula $C_3A = 2.65 (Al_2O_3) - 1.69 (Fe_2O_3)$] not more than 5 percent and specific surface determined by Blaines air permeability method not less than $2500 \text{ cm}^2/\text{g}$.

10. HYDROPHOBIC CEMENT

10.1 Hydrophobic Cement — Cement obtained by grinding ordinary Portland cement clinker with an additive which will impart to ground cement, a water repelling property which shall be destroyed only by wet attrition, such as in concrete mixer. The hydrophobic quality of cement would facilitate its storage for longer periods in extremely wet climatic conditions.

(Continued from page 2)

<i>Members</i>	<i>Representing</i>
SHRI A. P. MAHESHWARY	Rohtas Industries Ltd, Dalmianagar
SHRI P. B. PATIL	Gammon India Ltd, Bombay
SHRI RABINDER SINGH	National Buildings Organization
SHRI G. T. BHIDE (<i>Alternate</i>)	
SHRI E. K. RAMACHANDRAN	National Test House, Calcutta
SHRI D. M. SAVUR	The Hindustan Construction Co Ltd, Bombay
SO 1 DESIGN (PAVEMENT)	Engineer-in-Chief's Branch, Army Headquarters
SHRI B. P. MUKHERJEE (<i>Alternate</i>)	
SHRI K. A. SUBRAMANIAM	Cement Manufacturers Association, Bombay
DR P. K. MEHTA (<i>Alternate</i>)	
SUPERINTENDING ENGINEER (PLANNING & DESIGNS)	Public Works Department, Government of Madras
EXECUTIVE ENGINEER, BUILDING CENTRE DIVISION (<i>Alternate</i>)	
SHRI L. SWAROOP	Dalmia Cement (Bharat) Ltd, New Delhi
SHRI A. V. RAMANA (<i>Alternate</i>)	
SHRI S. P. VARMA	Directorate General of Technical Development
DR H. C. VESVESVARAYA	Cement Research Institute of India, New Delhi

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 331 01 31

Telegrams : Manaksansthe

331 13 75

(Common to all Offices)

Regional Offices :

	<i>Telephone</i>
Central : Manak Bhavan, 9, Bahadur Shah Zafar Marg. NEW DELHI 110002	{ 331 01 31 331 13 75
† Eastern : 1/14 C.I.T. Scheme VII M, V.J.P. Road, Maniktola, CALCUTTA 700054	37 86 62
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	2 18 43
Southern : C.I.T. Campus, IV Cross Road, MADRAS 600113	41 29 16
† Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	6 32 92 95

Branch Offices :

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	2 63 48
† Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE 560058	39 49 55
Gangotri Complex, 5th Floor, Bhadbhada Road, T.T. Nagar, BHOPAL 462003	55 40 21
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
Kalai Kathir Building, 6/48-A Avanesi Road, COIMBATORE 641037	2 67 05
Quality Marking Centre, N.H. IV, N.I.T., FARIDABAD 121001	—
Savitri Complex, 116 G. T. Road, GHAZIABAD 201001	8-71 19 96
53/5 Ward No. 29, R.G. Barua Road, 5th By-lane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg, (Nampally Station Road) HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	6 34 71
117/418 B Sarvodaya Nagar, KANPUR 208005	21 68 76
Plot No. A-9, House No. 561/63, Sindhu Nagar, Kanpur Road, LUCKNOW 226005	5 55 07
Patliputra Industrial Estate, PATNA 800013	6 23 05
District Industries Centre Complex, Bagh-e-Ali Maidan, SRINAGAR 190011	—
T. C. No. 14/1421, University P. O., Palayam, THIRUVANANTHAPURAM 695034	6 21 04
<i>Inspection Offices (With Sale Point) :</i>	
Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	52 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35
*Sales Office Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, CALCUTTA	27 68 00
† Sales Office is at Novelty Chambers, Grant Road, BOMBAY	89 65 28
‡ Sales Office is at Unity Building, Narasimharaja Square, BANGALORE	22 39 71

Reprography Unit, BIS, New Delhi, India