

*Indian Standard*METHODS OF TEST FOR  
DETERMINATION OF WATER SOLUBLE  
CHLORIDES IN CONCRETE ADMIXTURES

UDC 666.972.16:543.831 [546.131-2]



© Copyright 1973

**INDIAN STANDARDS INSTITUTION**  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110001

# Indian Standard

## METHODS OF TEST FOR DETERMINATION OF WATER SOLUBLE CHLORIDES IN CONCRETE ADMIXTURES

Cement and Concrete Sectional Committee, BDC 2

### Chairman

DR H. C. VISVESVARAYA

### Representing

Cement Research Institute of India, New Delhi

### Members

DR A. S. BHADURI

National Test House, Calcutta

SHRI E. K. RAMACHANDRAN

(Alternate)

SHRI A. K. CHATTERJI

Central Building Research Institute (CSIR),  
Roorkee

DR S. S. REHSI (Alternate)

DIRECTOR

Central Road Research Institute (CSIR), New  
Delhi

DR R. K. GHOSH (Alternate)

DIRECTOR (CSMRS)

Central Water & Power Commission, New Delhi

DEPUTY DIRECTOR (CSMRS)

(Alternate)

SHRI K. H. GANGWAL

Hyderabad Asbestos Cement Products Ltd,  
Hyderabad

SHRI K. C. GHOSAL

Alokudyog Services Ltd, New Delhi

SHRI A. K. BISWAS (Alternate)

DR R. K. GHOSH

Indian Roads Congress, New Delhi

DR R. R. HATTIANGADI

Associated Cement Companies Ltd, Bombay

SHRI P. J. JAGUS (Alternate)

JOINT DIRECTOR, STANDARDS  
(B & S)

Research, Designs & Standards Organization,  
Lucknow

DEPUTY DIRECTOR,  
STANDARDS (B & S) (Alternate)

SHRI S. B. JOSHI

S. B. Joshi & Co Ltd, Bombay

SHRI M. T. KANSE

Directorate General of Supplies & Disposals

SHRI S. L. KATHURIA

Roads Wing, Ministry of Transport & Shipping

SHRI S. R. KULKARNI

M. N. Dastur & Co (Private) Ltd, Calcutta

SHRI M. A. MEHTA

Concrete Association of India, Bombay

SHRI O. MUTHACHEN

Central Public Works Department

SUPERINTENDING ENGINEER

2ND CIRCLE (Alternate)

SHRI ERACH A. NADIRSHAH

Institution of Engineers (India), Calcutta

(Continued on page 2)

© Copyright 1973

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

( Continued from page 1 )

<i>Members</i>	<i>Representing</i>
SHRI K. K. NAMBIAR	In personal capacity ( ' Ramanalaya ' 11 First Crescent Park Road, Gandhinagar, Adyar, Madras )
BRIG NARESH PRASAD	Engineer-in-Chief's Branch, Army Headquarters
COL J. M. TOLANI ( Alternate )	
PROF G. S. RAMASWAMY	Structural Engineering Research Centre ( CSIR ), Roorkee
DR N. S. BHAL ( Alternate )	
DR A. V. R. RAO	National Buildings Organization, New Delhi
SHRI K. S. SRINIVASAN ( Alternate )	
SHRI G. S. M. RAO	Geological Survey of India, Nagpur
SHRI T. N. S. RAO	Gammon India Ltd, Bombay
SHRI S. R. PINHEIRO ( Alternate )	
SECRETARY	Central Board of Irrigation & Power, New Delhi
SHRI R. P. SHARMA	Irrigation & Power Research Institute, Amritsar
SHRI MOHINDER SINGH ( Alternate )	
SHRI G. B. SINGH	Hindustan Housing Factory Ltd, New Delhi
SHRI C. L. KASLIWAL ( Alternate )	
SHRI J. S. SINGHOTA	Beas Designs Organization, Nangal Township
SHRI T. C. GARG ( Alternate )	
SHRI R. K. SINHA	Indian Bureau of Mines, Nagpur
SHRI K. A. SUBRAMANIAM	India Cements Ltd, Madras
SHRI P. S. RAMACHANDRAN ( Alternate )	
SHRI L. SWAROOP	Dalmia Cement ( Bharat ) Ltd, New Delhi
SHRI A. V. RAMANA ( Alternate )	
SHRI D. AJITHA SIMHA, Director ( Civ Engg )	Director General, ISI ( Ex-officio Member )

*Secretary*

SHRI Y. R. TENEJA

Deputy Director ( Civ Engg ), ISI

Cement Subcommittee, BDC 2 : 1

*Convener*

DR R. R. HATTIANGADI                      Associated Cement Companies Ltd, Bombay

*Members*

SHRI V. B. DESAI	Hindustan Construction Co Ltd, Bombay
DIRECTOR ( C&MDD )	Central Water & Power Commission
DEPUTY DIRECTOR ( C&MDD ) ( Alternate )	
DR R. K. GHOSH	Central Road Research Institute ( CSIR ), New Delhi
SHRI P. GON	Hindustan Steel Ltd, Ranchi
SHRI P. J. JAGUS	Associated Cement Companies Ltd, Bombay

( Continued on page 8 )

# Indian Standard

## METHODS OF TEST FOR DETERMINATION OF WATER SOLUBLE CHLORIDES IN CONCRETE ADMIXTURES

### 0. FOREWORD

**0.1** This Indian Standard was adopted by the Indian Standards Institution on 23 March 1973, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

**0.2** Various types of concrete admixtures are being used in this country, such as accelerators, retarders, water-proofers and air entraining agents. Some of these admixtures are likely to contain water soluble chlorides which are likely to cause corrosion of reinforcement in the reinforced concrete. In fact the use of such chlorides containing admixtures has been prohibited by IS:456-1964\*. However, the option of using such admixtures is left to the engineer-in-charge who has to use his discretion on the basis of relevant data in respect of the admixtures. As information on the percentage of water soluble chlorides in the admixtures is of vital importance it is considered necessary to bring out a standard dealing with the methods of test for determination of water soluble chloride content in concrete admixtures.

**0.3** In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS:2-1960†.

---

### 1. SCOPE

**1.1** This standard specifies the following methods of test for determination of water soluble chlorides in concrete admixtures:

- a) Volumetric method,
- b) Gravimetric method, and
- c) Turbidimetric method.

\*Code of practice for plain and reinforced concrete (*second revision*).

†Rules for rounding off numerical values (*revised*).

## 2. SELECTION OF METHOD

**2.0** One of the three methods may be used appropriately depending on the concentration of the chlorides in the admixtures as per the declaration of the manufacturer.

**2.1** The volumetric method may be used when the chloride concentration is nearly 1 percent or above.

**2.2** The gravimetric method may be used when the chloride concentration is more than 2.5 percent.

**2.3** The turbidimetric method may be used when the concentration of chloride is as low as 2 ppm and above.

**2.4** Where a choice is open between volumetric and gravimetric methods volumetric method is preferable as it is quicker and less laborious. Turbidimetric method may be adopted when the chloride concentration is very low.

## 3. VOLUMETRIC METHOD

### 3.1 Reagents

**3.1.0** *Quality of Reagents*—Unless otherwise specified, pure chemicals and distilled water (see IS: 1070-1960\*) shall be employed in the tests.

NOTE—'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

**3.1.1** *Nitric Acid*—1:2.5—6 N.

**3.1.2** *Sodium or Potassium Chloride Solution (Standard)*—0.1 N.

**3.1.3** *Potassium Chromate Indicator Solution*

**3.1.4** *Silver Nitrate Solution*—0.1 N.

**3.1.4.1** *Preparation*—Weigh about 8.5 g of silver nitrate, dissolve in distilled water and make up to 500 ml in a volumetric flask.

**3.1.4.2** *Standardization*—Standardize the solution against 0.1 N sodium chloride or potassium chloride solution using potassium chromate solution as indicator. Adjust the normality exactly to 0.1.

**3.1.5** *Nitrobenzene*

**3.1.6** *Ferric Alum Indicator Solution*

**3.1.7** *Ammonium Thiocyanate Solution*—0.1 N.

---

\*Specification for water, distilled quality (revised).

**3.1.7.1 Preparation**—Weigh about 8.5 g of ammonium thiocyanate and dissolve it in 1 litre of water in a volumetric flask. Shake well, and standardize by titrating against 0.1 N silver nitrate solution using ferric alum solution as indicator. Adjust the normality exactly to 0.1.

## 3.2 Procedure

**3.2.1** Weigh accurately sufficient quantity of the admixture such that about 0.1 g of chloride is present in the sample. Add enough hot water so as to make a volume of 150 ml, stir until dissolution is complete. If there is insoluble matter, filter and wash with water. Make up the clear solution thus obtained to a volume of 250 ml with water, shake well.

**3.2.2** Pipette 50 ml of the solution into a 250-ml conical flask containing 5 ml of 6 N nitric acid. Add 10 to 15 ml of 0.1 N silver nitrate solution from the burette. Then add 2 to 3 ml of nitrobenzene and 1 ml ferric alum indicator and shake vigorously to coagulate the precipitate. Titrate the excess silver nitrate with 0.1 N ammonium thiocyanate until a permanent faint reddish brown colouration appears. Repeat the titration with another 50 ml portion.

**3.2.3** From the volume of silver nitrate ( $\text{AgNO}_3$ ) solution added subtract the volume of thiocyanate solution required. Take the average of the two determinations. Calculate the percentage of chloride (Cl) in the sample:

$$1 \text{ ml } 0.1 \text{ N AgNO}_3 = 0.003546 \text{ g, Cl}$$

## 4. GRAVIMETRIC METHOD

### 4.1 Reagents

**4.1.1** *Concentrated Nitric Acid*

**4.1.2** *Dilute Nitric Acid* — 1 : 50.

**4.1.3** *Silver Nitrate Solution* — approximately 0.1 N (see 3.1.4).

**4.1.4** *Dilute Hydrochloric Acid* — 1 : 100.

### 4.2 Procedure

**4.2.1** Weigh out accurately sufficient quantity of the admixture such that about 0.05 g of chloride is present in the sample. Add enough hot water so as to make a volume of 150 ml, stir until the dissolution is complete. Filter and wash with water if there is insoluble matter. Add 1 to 2 ml of concentrated nitric acid. Then add the silver nitrate solution slowly and with constant stirring until the precipitation is complete. Add a slight excess (5 to 10 ml) of the silver nitrate solution. Heat the suspension nearly to boiling, while stirring constantly and maintain it at

this temperature until the precipitate coagulates and the supernatant liquid is clear. Set aside the beaker in the dark for one hour and filter through a previously weighed sintered glass or porcelain crucible. Transfer the last traces of silver chloride adhering to the beaker with a policeman. Wash the precipitate in the crucible with 1:50 nitric acid added in small portions until 3 to 5 ml of the washings collected in a test tube give no turbidity with 1 or 2 drops of dilute hydrochloric acid. Dry the crucible and contents in an air-oven at 130 to 150°C for one hour. Allow to cool in a desiccator and weigh. Repeat the process of drying and cooling until constant weight is attained.

**4.2.2** Calculate the percentage of chloride in the sample:

$$0.1 \text{ g AgCl} = 0.024737 \text{ Cl}$$

## 5. TURBIDIMETRIC METHOD

### 5.1 Apparatus

#### 5.1.1 Turbidimeter

### 5.2 Reagents

#### 5.2.1 Dilute Nitric Acid — 1:3.

#### 5.2.2 Silver Nitrate Solution — See 4.1.3.

#### 5.2.3 Standard Sodium Chloride Solution

**5.2.3.1 Preparation** — Weigh accurately 0.1649 g of sodium chloride (previously dried at 105 to 110°C for 2 h) and dissolve in 1 000 ml of distilled water in a volumetric flask. This solution contains 100 ppm chloride, that is, 100 mg/l.

### 5.3 Procedure

**5.3.1 Calibration of the Turbidimeter** — Take 5 ml of dilute nitric acid in a 100-ml volumetric flask, add 5 ml of silver nitrate solution and make up the volume with distilled water. Shake well and use the solution as 'blank' for adjusting the 'zero' of the galvanometer. Take 20 ml of the standard sodium chloride solution in a 100-ml volumetric flask, add 5 ml of dilute nitric acid and 50 to 60 ml distilled water. Shake well and add 5 ml of silver nitrate solution and make up the volume with distilled water. Shake well and use this turbid solution to adjust the galvanometer deflection to full scale.

**5.3.1.1** Run in 1.0, 2.5, 5.0, 7.5, 10.0, 15.0, 17.5 and 20.0 ml standard chloride solution from a burette into separate 100-ml volumetric flasks. Take the first flask, add 5 ml of dilute nitric acid and 50 to 60 ml distilled water. Shake well, add 5 ml of silver nitrate solution and make up

the volume with distilled water. Shake well and measure the turbidity after checking the galvanometer 'zero' again. Repeat the above procedure with the remaining solutions.

**5.3.1.2** Plot the galvanometer readings against chloride concentration in ppm.

**5.3.2** *Determination of Chloride in the Test Sample*—Weigh accurately sufficient quantity of admixture such that it contains about 0.01 g of chloride and boil with 100 to 150 ml distilled water. Filter and wash with hot distilled water. Collect the filtrate and washings into a 500-ml volumetric flask and make up the volume. Take 50 ml (*see Note*) of this solution into a 100-ml volumetric flask, add 5 ml dilute nitric acid and 5 ml silver nitrate solution, and make up the volume with distilled water. Shake well and measure the turbidity after checking the galvanometer 'zero'. Read the chloride ion concentration in ppm from the calibration plot prepared earlier and then calculate the percentage of chloride in the sample.

$$\text{Percentage chloride} = \frac{\text{Weight of chloride in g}}{\text{Weight of the sample taken}} \times 100$$

NOTE—Suitable dilutions may have to be carried out such that the galvanometer reading falls within the range 2 to 15 ppm chloride whenever it is found necessary.



(Continued from page 2)

<i>Members</i>	<i>Representing</i>
JOINT DIRECTOR, RESEARCH ( B & S )	Research, Designs & Standards Organization ( Ministry of Railways )
ASSISTANT DIRECTOR, RE- SEARCH ( B & S ) ( <i>Alternate</i> )	
SHRI S. V. MAHESHWARY	Rohtas Industries Ltd, Dalmianagar
SHRI M. A. MEHTA	Concrete Association of India, Bombay
SHRI K. P. MOHIDEEN	Central Warehousing Corporation, New Delhi
SHRI K. K. NAMBIAR	In personal capacity ( ' Ramanalaya ' II First Crescen Park Road, Gandhinagar, Adyar, Madras )
SHRI E. K. RAMACHANDEAN	National Test House, Calcutta
DR A. V. R. RAO	National Buildings Organization, New Delhi
SHRI G. T. BHIDE ( <i>Alternate</i> )	
SHRI S. A. REDDY	Gammon India Ltd, Bombay
SHRI R. P. SHARMA	Irrigation & Power Research Institute, Amritsar
SHRI MOHINDER SINGH ( <i>Alternate</i> )	
SHRI K. K. SOMANI	Shree Digvijay Cement Co Ltd, Bombay
SHRI R. K. GATTANI ( <i>Alternate</i> )	
SHRI K. A. SUBRAMANIAM	Cement Manufacturers Association, Bombay
SUPERINTENDING ENGINEER ( PLANNING & DESIGNS CIRCLE )	Public Works Department, Government of Tamil Nadu
EXECUTIVE ENGINEER, BUILD- ING CENTRE DIVISION ( <i>Alternate</i> )	
SHRI L. SWAROOP	Dalmia Cement ( Bharat ) Ltd, New Delhi
SHRI A. V. RAMANA ( <i>Alternate</i> )	
DR C. A. TANEJA	Central Building Research Institute ( CSIR ), Roorkee
DR R. K. DATTA ( <i>Alternate</i> )	
COL J. M. TOLANI	Engineer-in-Chief's Branch, Army Headquarters
MAJ D. D. SHARMA ( <i>Alternate</i> )	
DR S. P. VARMA	Directorate General of Technical Development
SHRI N. G. BAAK ( <i>Alternate</i> )	
DR H. C. VISVESVARAYA	Cement Research Institute of India, New Delhi
DR S. K. CHOPRA ( <i>Alternate</i> )	

# INDIAN STANDARDS

## ON

## CEMENT

IS:

- 269-1967 Ordinary, rapid-hardening and low heat Portland cement (*second revision*)  
455-1967 Portland blastfurnace slag cement (*second revision*)  
650-1966 Standard sand for testing of cement (*first revision*)  
1489-1967 Portland-pozzolana cement (*first revision*)  
2645-1964 Integral cement waterproofing compounds  
3466-1967 Masonry cement (*first revision*)  
4031-1968 Methods of physical tests for hydraulic cement  
4032-1968 Method of chemical analysis of hydraulic cement  
4845-1968 Definitions and terminology relating to hydraulic cement  
6452-1972 High alumina cement for structural use

---

### INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi, 110001

Telephone : 27 01 31 ( 20 lines )

Telegrams : Manaksanstha

#### Branch Offices:

	Telephone
'Sadhna', Nurmohamed Shaikh Marg, Khanpur, Ahmedabad 380001	2 03 91
F Block, Unity Bldg, Narasimharaja Square, Bangalore 560002	2 76 49
634 Sardar Vallabhbhai Patel Road, Bombay 400007	35 69 44
5 Chowringhee Approach, Calcutta 700013	23-08 02
5-9-201/2-A ( First Floor ), Chirag Ali Lane, Hyderabad 500001	3 44 35
117/418 B Sarvodaya Nagar, Kanpur 208005	82 72
54 General Patters Road, Madras 600002	8 72 78